Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2018-02-06-10** **Date: 09-02-18**
Customer	:	Assistant Executive Engineer, Yelahanka Satellite Town Sub Division,
Address	:	Yelahanka Satellite Town Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of CC roads and drains in Sanitary core in ward No.04 Yelahanka Upanagara.
Agency	:	Sri.Y.B Ramesh, No.34, Down Bazar Road, Yelahanka, Bangalore-64.
Customer's Reference	:	EE(YNK.D)E-PMT-13/W.O/133/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-02-18
Sample ID No	:	2018-02-06-10 /01
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	07-02-18
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	2.65	–
2	Finess by Air permeablity method (m^2/kg,Min)	286.4	225m^2/kg, Min
3	Density (gm/cc)	3.14	–
4	Standard Consistency (%)	28.5%	Not specified
5	Initial Setting time	185 minutes	Not less than 30 minutes
6	Final Setting time	280 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	2mm	Not more than 10 mm

AB-4

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO BANGALORE Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****